

EXEMPLES : REDRAW WIRE

Description : Round galvanised or phosphated wire due for redrawing.

Steel : 0,03 to 0,82 % carbon.

Tensite strenght : 400 to 1400 N/mm².

Coating : - Electro-galvanised as per international standards.

- Liquor finish.
- Coppered.
- Phosphated.

This wire is specially treated to provide the smoothest possible surfaces for high speed feeding.



Diameter : 1,50 to 3,50 mm.

Tolerances : ± 0,01 to ± 0,05 mm according to wire diameter.

Packaging : Orbit wound coils from 250 to 1 200 Kg.

Strapped or on pallets with or without lifting rings.

	ORBIT WOUND COILS
Type	PC
Weight of wire (Kg)	250 / 1200
Ø outside dia. (mm)	800
Ø inside dia. (mm)	350 / 400
Height (mm)	300 / 900

Please note all weights shown are approximate, and issued for guidance only. All measurement are metric.

Unwinding : Dynamic or Static. Unwinding systems are available on request.

Important characteristics : It is recommended to specify the diameter of your wire requirements in mm.

CONFLANDEY reserves the right to modify any of the above details in the pursuit of improvements in quality and service.

CONFLANDEY INDUSTRIES

3 RUE DU CHATEAU AMONCOURT - BP 21 70170 PORT SUR SAONE - FRANCE

Tél. : 33 (3) 84.91.38.38 - FAX : 33 (3) 84.91.47.04

contact@conflandey-industries.com

CONFLANDEY reserves the right to modify any of the above details in the pursuit of improvements in quality and service.

CONFLANDEY INDUSTRIES

3 RUE DU CHATEAU AMONCOURT - BP 21 70170 PORT SUR SAONE - FRANCE

Tél. : 33 (3) 84.91.38.38 - FAX : 33 (3) 84.91.47.04

contact@conflandey-industries.com